

KOREA TACONIC CO., LTD.

2Na 104 Exclusive Complex for Foreigners 712 Paeksok-dong,

Cheonan-si, Chungchongnam-do, Korea

TEL : +82-41-522-1858, FAX : +82-41-522-1857

CUSTOMER :

QUANTITY :

TECHNICAL SPECIFICATION DATA SHEET

ITEM	DATA	SPECIFICATION	TEST METHOD
Product No.	7058		
Reinforcing Fabric	Glass Fabric		
LOT No			
Coating Type	P.T.F.E		
% Coating	60	± 2	
Thickness(mm)	0.128		Nominal
Total Coated Weight(g/sqm)		$272 \pm 5\%$	
Tensile Strength(N/5 cm) : Warp		Min. 800	BS 3424 Part 4 Method 6
Tear Strength(N)		Min. 10	BS 7304 Part 4
Dielectric Breakdown(KV)		Min. 2.2	BS 2782 Part 2 Method 220
Operating Temperature(°C)	-73 ~ +260		
Appearance	Good		

Date :

Signed _____

K.Y.Park

IPD Technical Manager

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control.